

今すぐ木陰 検査結果(参考値)透過率[%]

波長[nm]	測定値	測定値	計算値	測定値	計算値	波長[nm]	測定値	測定値	計算値	測定値	計算値
	ガラス	ガラス+1枚	ガラス+1枚	ガラス+2枚	ガラス+2枚		ガラス	ガラス+1枚	ガラス+1枚	ガラス+2枚	ガラス+2枚
250	1.4	0.5	0.510	0.2	0.185	1800	92.5	48.3	0.471	26.2	0.002
300	38.3	13.2	13.597	4.4	4.827	1850	92.3	48.8	12.550	27	1.706
350	90.2	31.4	31.841	10.7	11.240	1900	92.2	49.3	29.357	27.7	9.347
400	91.4	31.9	32.356	11	11.454	1950	92.3	49.7	29.864	28.3	9.663
450	91.4	32.5	32.904	11.4	11.845	2000	92.2	50.2	30.337	28.8	9.982
500	91.5	33.2	33.672	12	12.391	2050	92.1	50.7	31.012	29.2	10.442
550	91.6	34.1	34.533	12.7	13.019	2100	91.9	50.9	31.736	29.7	10.959
600	91.7	34.9	35.488	13.3	13.734	2150	91.8	51.1	32.578	30.2	11.561
650	91.6	35.8	36.182	14	14.292	2200	91.3	51.2	33.034	30.1	11.952
700	91.6	36.5	36.915	14.7	14.877	2250	91.1	50	33.629	29.5	12.414
750	91.7	37.4	37.780	15.1	15.566	2300	91.1	44.8	34.418	23.6	13.003
800	91.8	38.1	38.556	15.8	16.194	2350	91.2	42.8	35.163	21.5	13.557
850	91.7	38.8	39.156	16.3	16.720	2400	91	44.9	35.632	24	13.952
900	91.9	39.6	39.977	17	17.390	2450	90.6	45.5	36.219	24.7	14.479
950	91.9	40.1	40.528	17.5	17.873	2500	90.3	48.4	36.597	27.8	14.832
1000	92.1	40.8	41.261	18.1	18.485						
1050	92.2	41.4	41.859	18.7	19.004						
1100	92.2	42	42.504	19.3	19.594						
1150	92.3	42.5	43.012	19.9	20.043						
1200	92.3	42.9	43.381	20.3	20.389						
1250	92.4	43.7	44.167	21	21.112						
1300	92.4	44.3	44.814	21.7	21.735						
1350	92.4	44.8	45.276	22.2	22.185						
1400	92.4	45	45.553	22.5	22.458						
1450	92.4	45.6	46.108	23.2	23.008						
1500	92.5	46.2	46.713	23.8	23.590						
1550	92.6	46.8	47.319	24.4	24.180						
1600	92.5	47.2	47.730	24.9	24.629						
1600	92.5	47.2	48.100	24.9	25.012						
1650	92.5	47.6	47.360	25.5	24.248						
1700	92.6	46.8	47.874	24.6	24.751						
1750	92.6	47.4	48.893	25.2	25.815						

